

ERACLENE®

BB 82

HDPE

High density polyethylene

Eraclene BB 82 is a high density polyethylene resin (HDPE), with antioxidants, suitable for blow moulding application. It is especially recommended for the production of containers up to 220 liters.

Main Application

Eraclene BB 82 provides an excellent combination of extrudability and parison stability, which, in turn, allows to obtain a uniform wall thickness in large blow moulded parts. Eraclene BB 82 is ideal for the production of various industrial containers. Its broad molecular weight distribution leads to an outstanding environmental stress cracking resistance (ESCR) in combination with a good rigidity.

Main Properties

Resin Properties	Value	Unit	Test Method
Melt Flow Rate (190 °C/2,16 kg)	-	g/10min	ISO 1133
Melt Flow Rate (190 °C/5 kg)	0,15	g/10min	ISO 1133
Melt Flow Rate (190 °C/21,6 kg)	5	g/10min	ISO 1133
Density	0.954	g/cm ³	ISO 1183
Melting point	132	°C	Internal method
Brittleness temperature	< -60	°C	ASTM D 746
Vicat softening point (1 kg)	127	°C	ISO 306/A

Mechanical Properties *	Value	Unit	Test Method
Tensile stress at yield	27	MPa	ISO 527
Tensile stress at break	30	MPa	ISO 527
Tensile strain at yield	-	%	ISO 527
Elongation at break	> 600	%	ISO 527
Flexural modulus	1200	MPa	ISO 178
Hardness Shore D	65	-	ISO 868 A
Falling Weight:	-	J	ISO 6603-2
Izod impact strength, notched	**	J/m	ASTM D 256
Environmental Stress Cracking Resistance (ESCR) ***	> 750	h	ASTM D 1693 (B)

(*) Values are referred to compression moulded specimens. Actual properties are typical and may vary depending upon operating conditions.

(**) No break.

(***) 100% surface-active agent – Condition B.

Processing notes

Eraclene BB 82 can be processed in the latest blow moulding machines with excellent results. Moulded parts exhibit outstanding surface quality.

Typical moulding conditions:

Temperature setting, barrel zone 1	(°C) 180 - 190
Temperature setting, barrel zone 2	(°C) 1-) - &\$)
Temperature setting, head and die	(°C) % -) - 2\$)
Operation temperature	(°C) 20) - 21)

Storage and Handling

Eraclene BB 82 is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletised polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practised throughout your facility.

The product should be stored in dry conditions at temperatures below 50 °C and protected from sunlight.

Improper storage can initiate degradation which results in odour generation, colour changes and can have negative effects on the physical properties of the product.

Before using this product it is recommended to read and understand the relevant Safety Data Sheet.

Availability

Contact the versalis sales office nearest to you regarding availability and your specific application requirements.

Food Contact Status

Eraclene BB 82 complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

HY W\ b] AWU b U [Y a Y D c m Y h \ m` U b X` d d `] WU h] c b g ` 8 Y j Y ` c d a Y b h

7 Y b h f c ! G i i f X c d U 5` a Y f] W\ Y

Versalis S.p.A.

Head Office

Piazza Boldrini 1 - 20097 San Donato Milanese (MI) - Italy
tel. +39 0252032998 +39 0252042262
+39 0252042005 +39 0252032072
+39 0252042984

Mantova

Via Taliercio 14 - 46100 Mantova (MN) - Italy
tel. +39 0376305520 +39 0376305741

B c f X i f c d U F` C K

Versalis S.p.A.

4531 Route des Dunes - CS 20060 Mardyck
59279 Dunkerque - France
tel. +33 328235516 +33 328235512

Duesselderfer Str. 13 65760
Eschborn - Germany
tel. +49 15140260561

IMPORTANT: please consult the relevant safety data sheet for more detailed information. The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information and data.

versalis is available to provide the guaranteed values for each product on demand.

DISCLAIMER: it is the sole responsibility of the end-user to determine the safety, the regulatory compliance as well as the technical suitability of the product for the intended application. The product is not intended for use in medical devices and pharmaceutical applications; Versalis declines all responsibility and cannot be held liable in case of use in the above mentioned applications.