



MAIN APPLICATIONS

The main properties of Eraclene DB 506 BCA are emphasized when it is used for production of drip irrigation pipe. The balanced molecular weight distribution, density and the low content of gels are successfully combined in order to provide excellent mechanical properties, sealability, melt strenght and drawability at high extrusion rate. can be easily used in blend with LLDPE and LDPE grades to modify the final properties of the drip irrigation pipe accordng to the specific needs. For outdoor application, it is strongly suggested to add Anti UV. The combined usage of these additives together with Carbon Black can provide outstanding resistance to UV radiation.

PROCESSING NOTES

Eraclene DB 506 BCA is readily processable by conventional equipment. It is suggested to be used a mixing screw with a flat or slightly growing temperature profile from 190°C up to 230°C. The best balance of processing and properties of the drip irrigation pipe is obtained with a die gap between 1,5 mm and 2,5 mm.

STORAGE AND HANDLING

Eraclene DB 506 BCA is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletized polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practiced throughout your facility. The product should be stored in dry conditions at temperatures below 50°C and protected from sunlight. Improper storage can initiate degradation which results in odor generation, color changes and can have negative effects on the physical properties of the product. Before using this product, it is recommended to read and understand the relevant Safety Data Sheet.

AVAILABILITY

Contact the Versalis sales office nearest to you regarding availability and your specific application requirements.

FOOD CONTACT STATUS

Eraclene DB 506 BCA complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

TECHNICAL MANAGEMENT DC

Center Europe Americas

Versalis .p.A

head office
Pia a Boldrini,
an Donato ilanese taly
tel.
tel.

antova
Via Taliercio
antova taly
tel. #

North Europe RDW

J Y f g U `] g G " d " 5 "

() % F c i X Y g i b Y l g 7 G & S S U f X m W _) - & + -
8 i b _ Y f e i U b W Y
h Y ` " ' & , & ')) % * # ' ' & , & ')) % &

8 i Y g g Y ` X G H Z Y f
*) + * \$ 9 g W \ V c f b Ä 8 Y i h g W \ ` U b X
h Y ` (- %) % (\$ & * \$) * %

IMPORTANT: consult the relevant safety data sheet for more detailed information. The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information and data. Versalis is available to provide the guaranteed values for each product on demand

DISCLAIMER: sole responsibility of the end-user to determine the safety, the regulatory compliance as well as the technical suitability of the product for the intended application. The product is not intended for use in medical devices and pharmaceutical applications; Versalis declines all responsibility and cannot be held liable in case of use in the above-mentioned applications.