

MAIN APPLICATIONS

Clearflex FG 336 A BA is recommended for shipping sacks where the perfect balance between adittivation (interms of slip and antiblocking) and mechanical performances leads to the manufacture of a tough and easypeelable film. Moreover for its sealing characteristics, together with low temperature mechanical resistance, Clearflex FG 336 A BA is suggested for the production of freezer bags, either in coextrusion and in blend with LDPE.

PROCESSING NOTES

Clearflex FG 336 A BA is easily processable using blown film technology. Melt temperature should be between 190°C and 230°C. Recommended thickness: 10 - 50 µm.

STORAGE AND HANDLING

Clearflex FG 336 A BA is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletized polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practiced throughout your facility. The product should be stored in dry conditions at temperatures below 50°C and protected from sunlight. Improper storage can initiate degradation which results in odor generation, color changes and can have negative effects on the physical properties of the product. Before using this product, it is recommended to read and understand the relevant Safety Data Sheet.

AVAILABILITY

Contact the Versalis sales office nearest to you regarding availability and your specific application requirements.

FOOD CONTACT STATUS

Clearflex FG 336 A BA complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

TECHNICAL MANAGEMENT

Characteristics

Material

<M>X C<M>VY
 D<M>U<M>nnU6cXf<M>] %
 &\$- GUb8cbUhcAUbyX= ! hUm
 h%&\$\$-:(\$)&(\$&*&
 h%&(\$&\$\$)&\$\$&
 '\$)&\$\$-(

AUbh<M>cJ U
 JUHUW<M>%(
 hY: \$*&\$ # \$

N h p d W/

M

Y % Y M G \$ \$
 M ! W/
 M ' M

M %
 M/
 M

IMPORTANT: please consult the relevant safety data sheet for more detailed information. The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information and data. Versalis is available to provide the guaranteed values for each product on demand
 DISCLAIMER: it is the sole responsibility of the end-user to determine the safety, the regulatory compliance as well as the technical suitability of the product for the intended application. The product is not intended for use in medical devices and pharmaceutical applications; Versalis declines all responsibility and cannot be held liable in case of use in the above-mentioned applications.

> UbiUfm 202