

## FLEXIRENE®

## FH 56 A

LLDPE

Linear low density polyethylene

Flexirene FH 56 A is a butene copolymer with medium density (C4-LLDPE), with antioxidants and processing aid, suitable for blown film extrusion.

Films manufactured with Flexirene FH 56 A are characterised by an optimum balance between mechanical properties (stiffness) and sealing properties.

### Main Applications

Flexirene FH 56 A is recommended for the production of general purpose film, both in blend and in coextrusion with LDPE. It is also used for the production of nets because of its perfect balance between rigidity and processability.

### Main Properties

| Resin Properties                | Value | Unit              | Test Method     |
|---------------------------------|-------|-------------------|-----------------|
| Melt Flow Rate (190 °C/2,16 kg) | 1,4   | g/10min           | ISO 1133        |
| Melt Flow Rate (190 °C/5 kg)    | -     | g/10min           | ISO 1133        |
| Melt Flow Rate (190 °C/21,6 kg) | -     | g/10min           | ISO 1133        |
| Density                         | 0,934 | g/cm <sup>3</sup> | ISO 1183        |
| Melting Point                   | 126   | °C                | Internal method |
| Brittleness temperature         | < -70 | °C                | ASTM D 746      |
| Vicat softening point (1 kg)    | 117   | °C                | ISO 306/A       |

  

| Film Properties *                      | Value   | Unit   | Test Method  |
|--|---------|--------|--------------|
| Tensile stress at yield MD             | 16      | MPa    | ISO 527-3    |
| Tensile stress at yield TD             | 18      | MPa    | ISO 527-3    |
| Tensile stress at break MD             | 40      | MPa    | ISO 527-3    |
| Tensile stress at break TD             | 32      | MPa    | ISO 527-3    |
| Elongation at break MD                 | 650     | %      | ISO 527-3    |
| Elongation at break TD                 | 800     | %      | ISO 527-3    |
| 1% Secant modulus MD                   | 390     | MPa    | ISO 527-3    |
| 1% Secant modulus TD                   | 450     | MPa    | ISO 527-3    |
| Elmendorf tear resistance MD           | 7       | N/mm   | ISO 6383-2   |
| Elmendorf tear resistance TD           | 60      | N/mm   | ISO 6383-2   |
| Impact resistance F50 (Dart Drop Test) | 55      | g      | ISO 7765-1/A |
| Dynamic coefficient of friction (COF)  | > 0,5   | -      | ISO 8295     |
| Haze                                   | 14      | %      | ISO 14782    |
| Gloss, 45°                             | 50      | %      | ASTM D 2457  |
| Recommended film thickness             | 10 ÷ 50 | micron | -            |

(\* ) Typical value for a film extruded between 190 - 230 °C, with BUR 2,5, thickness 25 µm. Actual properties are typical and may vary depending upon operating conditions and additive package.

## Processing notes

Flexirene FH 56 A is easily processable using blown film technology. Melt temperature should be between 190 °C and 230 °C. The recommended thickness is from 10 to 50 µm.

## Storage and Handling

Flexirene FH 56 A is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletised polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practised throughout your facility.

The product should be stored in dry conditions at temperatures below 50 °C and protected from sunlight.

Improper storage can initiate degradation which results in odour generation, colour changes and can have negative effects on the physical properties of the product.

Before using this product it is recommended to read and understand the relevant Safety Data Sheet.

## Availability

Contact the Versalis sales office nearest to you regarding availability and your specific application requirements.

## Food Contact Status

Flexirene FH 56 A complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

## Technical Management Polyethylene

### Center and South Europe and Americas

Versalis S.p.A.

Head Office

Piazza Boldrini 1 - 20097 San Donato Milanese (MI) - Italy

tel. +39 0252032998 +39 0252042262

+39 0252042005 +39 0252032072

+39 0252042984

Mantova

Via Taliercio 14 - 46100 Mantova (MN) - Italy

tel. +39 0376305520 +39 0376305620

### North Europe and ROW

Versalis S.p.A.

4531 Route des Dunes - CS 20060 Mardyck

59279 Dunkerque - France

tel. +33 328235516 +33 328235512

Duesselder Str. 13 65760

Eschborn - Germany

tel. +49 15140260561

**IMPORTANT:** please consult the relevant safety data sheet for more detailed information. The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information and data. Versalis is available to provide the guaranteed values for each product on demand.

**DISCLAIMER:** it is the sole responsibility of the end-user to determine the safety, the regulatory compliance as well as the technical suitability of the product for the intended application. The product is not intended for use in medical devices and pharmaceutical applications; Versalis declines all responsibility and cannot be held liable in case of use in the above mentioned applications.