

## FLEXIRENE<sup>®</sup>

## MS 40 A

LLDPE

Linear low density polyethylene

Flexirene MS 40 A is a linear low density polyethylene (LLDPE) with antioxidants, suitable for injection moulding application.

Parts made by Flexirene MS 40 A are characterised by a good balance between impact resistance and rigidity.

### Main Application

Flexirene MS 40 A is recommended for the production of large sized articles, houseware and toys. Flexirene MS 40 A is characterized by a high flowability which make it ideal for masterbatches preparation for LDPE and LLDPE.

### Main Properties

#### Resin Properties

|                                 | Value | Unit              | Test Method     |
|---------------------------------|-------|-------------------|-----------------|
| Melt Flow Rate (190 °C/2.16 kg) | 27    | g/10min           | ISO 1133        |
| Melt Flow Rate (190 °C/5 kg)    | -     | g/10min           | ISO 1133        |
| Melt Flow Rate (190 °C/21.6 kg) | -     | g/10min           | ISO 1133        |
| Density                         | 0.930 | g/cm <sup>3</sup> | ISO 1183        |
| Melting point                   | 121   | °C                | Internal method |
| Brittleness temperature         | <- 70 | °C                | ASTM D 746      |
| Vicat softening point (1 kg)    | 103   | °C                | ISO 306/A       |

#### Mechanical Properties \*

|   | Value | Unit | Test Method    |
|---|-------|------|----------------|
| Tensile stress at yield                         | 11    | MPa  | ISO 527        |
| Tensile stress at break                         | 12    | MPa  | ISO 527        |
| Tensile strain at yield                         | -     | %    | ISO 527        |
| Elongation at break                             | > 400 | %    | ISO 527        |
| Flexural modulus                                | 300   | MPa  | ISO 178        |
| Hardness Shore D                                | 52    | -    | ISO 868 A      |
| Falling Weight:                                 | -     | J    | ISO 6603-2     |
| Izod impact strength, notched                   | -     | J/m  | ASTM D 256     |
| Environmental Stress Cracking Resistance (ESCR) | -     | h    | ASTM D 1693(B) |

(\*) Values are referred to injection moulded specimens. Actual properties are typical and may vary depending upon operating conditions.

## Processing notes

Flexirene MS 40 A is easy to mould with the newest injection moulding machines. Results are excellent.

Typical processing conditions (\*)

Temperature profile of the barrel (°C) 160 - 210

Temperature of the mould (°C) 10 - 40

(\*) Processing conditions are depending on several parameters: the shape of the part to be manufactured, the localisation of the injection point, the injection moulding machine and the cooling of the mould.

## Storage and Handling

Flexirene MS 40 A is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletised polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practised throughout your facility.

The product should be stored in dry conditions at temperatures below 50°C and protected from sunlight.

Improper storage can initiate degradation which results in odour generation, colour changes and can have negative effects on the physical properties of the product.

Before using this product it is recommended to read and understand the relevant Safety Data Sheet.

## Availability

Contact the versalis sales office nearest to you regarding availability and your specific application requirements.

## Food Contact Status

Flexirene MS 40 A complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

## Technical Management Polietilene and Client Relationship

### Center and South Europe and Americas

Versalis S.p.A.

Head Office

Piazza Boldrini, 1

20097 San Donato Milanese (MI) - Italy

tel. +39 02 52032087 + 39 02 52032190

tel. +39 02 52042005 + 39 02 52032319

Mantova

Via Taliercio 14 - 46100 Mantova (MN) - Italy

tel. +39 03 76305520 +39 03 76305741

### North Europe and ROW

Versalis S.p.A.

4531 Route des Dunes - CS 20060 Mardyck 59279

Dunkerque - France

tel. +33 328235516

Duesseldorfer Str. 13

65760 Eschborn - Deutschland

tel +49 6196492249

**IMPORTANT:** please consult the relevant safety data sheet for more detailed information. The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information and data.

versalis is available to provide the guaranteed values for each product on demand.

**DISCLAIMER:** it is the sole responsibility of the end-user to determine the safety, the regulatory compliance as well as the technical suitability of the product for the intended application. The product is not intended for use in medical devices and pharmaceutical applications; Versalis declines all responsibility and cannot be held liable in case of use in the above mentioned applications.