





MAIN APPLICATIONS

Flexirene FG 20 F BA is recommended for the production of general purpose film, in blend or coextrusion with LDPE.

PROCESSING NOTES

Flexirene FG 20 F BA is easily processable using blown film technology. Melt temperature should be between 190 °C and 230 °C. Recommended thickness: 15 - 50 µm.

STORAGE AND HANDLING

Flexirene FG 20 F BA is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletized polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practiced throughout your facility. The product should be stored in dry conditions at temperatures below 50°C and protected from sunlight. Improper storage can initiate degradation which results in odor generation, color changes and can have negative effects on the physical properties of the product. Before using this product, it is recommended to read and understand the relevant Safety Data Sheet.

AVAILABILITY

Contact the Versalis sales office nearest to you regarding availability and your specific application requirements.

FOOD CONTACT STATUS

Flexirene FG 20 F BA complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

TECHNICAL MANAGEMENT DATA

Chemical name

Flexirene FG 20

Chemical structure information

Product code and identification

Other relevant information

Physical properties

Chemical composition

Physical properties

IMPORTANT INFORMATION: This document contains confidential information. It is intended for internal use only. It is not to be distributed outside the company without the express written consent of Versalis. All rights reserved.

DISCLAIMER: The information provided in this document is for informational purposes only and does not constitute an offer or a contract. The user assumes all responsibility for the use of the product. Versalis is not liable for any damages, including consequential damages, arising from the use of the product.