



## Technical Data Sheet



# Versalis Revive® EPS 3000 AE

## EPS

Expandable Polystyrene

Versalis Revive® EPS 3000 AE is a new Versalis expandable polystyrene developed for a more sustainable insulation. It contains 15% of post-consumer EPS coming from food packaging, household appliance packaging and seedtrays in accordance with UNI 10667/10 and certified Plastica Seconda Vita (PSV).

Main Properties	Units	Typical Values
Bulk density	kg/m <sup>3</sup>	590 - 630
Particle size	mm	0,7 - 1,1
Minimum apparent density		
• On a continuous pre-expander after one expansion	kg/m <sup>3</sup>	18
• On a discontinuous pre-expander after one expansion	kg/m <sup>3</sup>	17
Density range normally used	kg/m <sup>3</sup>	15 - 30

### Key Features

Versalis Revive® EPS 3000 AE contains a flame-retardant additive which makes it suitable for building applications. The narrow bead size distribution leads to good filling of the moulds and allows to obtain a very smooth surface. The colour of the raw material may change depending on the secondary raw material, once expanded the color will be pearl white.

Versalis Revive® EPS 3000 AE complies with the CAM requirements (Italian Minimum Environmental Criteria).

### Main Applications

Versalis Revive® EPS 3000 AE is used to produce:

- Shape or block moulding panels for ETICS
- Roof insulation panels
- Floor panels
- Cavity wall

### Processing

Versalis Revive® EPS 3000 AE can be processed with standard technologies using process conditions similar to those of traditional products.

Versalis Revive® EPS 3000 AE can be moulded to produce shaped articles and blocks.

### Certifications

Versalis Revive® EPS 3000 AE is certified Plastica Seconda Vita – PSV.

Versalis Revive® EPS 3000 AE is certified EuroClass E and LNE.

### Storage Conditions

It is recommended to keep the product in a dry well-ventilated store between 15-20°C.

For product packed in octabins, the guaranteed shelf-life is one month in the mentioned conditions.

During the processing of Expandable Polystyrene any sparks or open flames must be avoided and smoking should be forbidden. Adequate electrical grounding of machinery and of pneumatic conveyance lines is recommended.

The boards and moulded parts made of Revive® EPS 3000 AE should not be exposed to solar radiation and not packed in transparent film. The use of an opaque or white film is strongly recommended.

For further information concerning storage, packaging and processing precautions please refer to the relative Safety Data Sheet.

The information and data presented herein are to the best of our knowledge, true and accurate, but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information data.

® Registered Trademark