NOVEL TECHNOLOGY:
VERSALIS RECYCLED POLYPROPYLENE (r-PP) DECONTAMINATION TECHNOLOGY

This document is CONFIDENTIAL and is property of Versalis S.p.A. It shall neither be divulged to any third party nor used for purposes other than those for which it has been provided. Unless expressly authorized in writing by Versalis S.p.A. its reproduction is prohibited.

SUMMARY

ARTICLE 10.1 3

ARTICLE 10.2 3

1. FOREWORDS 4

2. CHARACTERIZATION OF INPUT MATERIAL 4

3. CHARACTERIZATION OF THE NOVEL TECHNOLOGY (ART. 10.3.A) 6

4. SCIENTIFIC EVIDENCE AND STUDIES ABOUT THE DECONTAMINATION TECHNOLOGY (ART. 10.3.C) 7

5. DESCRIPTION OF TYPICAL RECYCLING PROCESS USING THE TECHNOLOGY (ART. 10.3.D) 15

6. SUITABILITY OF THE RECYCLING TECHNOLOGY AND COMPLIANCE WITH THE RELEVANT PROVISIONS ON FOOD CONTACT MATERIALS AND ARTICLES 16

7. DIFFERENCES FROM EXISTING TECHNOLOGIES (ART. 10.3.E) 16

8. SUMMARY OF EVALUATION CRITERIA (ART. 10.3.F) 16

9. LIST OF DECONTAMINATION INSTALLATIONS (ART. 10.3.G) 16

This document is CONFIDENTIAL and is property of Versalis S.p.A. It shall neither be divulged to any third party nor used for purposes other than those for which it has been provided. Unless expressly authorized in writing by Versalis S.p.A. its reproduction is prohibited.

ARTICLE 10.1

Developer
Versalis S.p.A
Viale Alcide De Gasperi, 2 - 20097 San Donato Milanese (MI), Milan, Italy

ARTICLE 10.2

Versalis S.p.A
Nicola Fiorotto – Research, Development & Technological Innovation Head
Phone: +39 345 5904415
Email: Nicola.fiorotto@versalis.eni.com
Registered mail: ricerca_sviluppo_hq@pec.versalis.eni.com
Web-site: www.eni.versalis.com

Territory Competent Authority:
ITALY Ministero della Salute - Regione Lombardia
Viale Giorgio Ribotta, 5 - 00144 Roma
www.salute.gov.it

ATS Val Padana
Via dei Toscani, 1 - 46100 Mantova
www.ats-valpadana.it

Commission:
Directorate-General for Health and Food Safety (DG SANTE)
1049 Bruxelles/Brussel - Belgium

Uniform Resource Locator ("URL"):
https://versalis.eni.com/it-IT/innovazione/r-polymers-novel-technology.html

Novel Technology summary – "Recycled Polypropylene (r-PP) Decontamination Technology"
Versalis notifies the novel technology "Recycled Polypropylene (r-PP) Decontamination Technology" as "developer" under the Regulation 2022/1616. Recyclers using Versalis novel technology will produce pellets of decontaminated r-PP suitable to be used in food packaging applications in direct contact with food, according to the application-specific recycled content limits supported by the safety evaluation shown in the following. Polypropylene is a well-suited material for mechanical recycling, however recycling in food contact applications requires a validated process able to fulfil EFSA requirements for recycled plastics in direct food contact.

The notified technology comprises the melt-decontamination step and the associated melt-transfer, control, monitoring, diversion and segregation functions required to ensure that only material processed within the validated operating window may be designated for food-contact use. Collection, sorting, grinding, washing and drying are upstream pre-treatment operations and remain mandatory prerequisites governed by a quality-assurance system. Melt filtration, extrusion, pelletizing and any downstream post-treatment shall be operated under documented conditions that do not compromise the validated decontamination performance.

This document is CONFIDENTIAL and is property of Versalis S.p.A. It shall neither be divulged to any third party nor used for purposes other than those for which it has been provided. Unless expressly authorized in writing by Versalis S.p.A. its reproduction is prohibited.

The Versalis Novel Decontamination Technology, thanks to a proprietary special design of some items and properly managing process parameters, as temperature, pressure and residence time, is able to clean efficiently recycled polypropylene (r-PP) and so to reduce contaminants below the target level required for the intended direct food contact applications, when used according to the application-specific recycled content limits defined. The input material consists of PP objects (mainly closures/caps) from separate collection (e.g. curbside), so called post-consumer PP. A high share of food contact PP is obtained by the selection of the proper source and by accurate sorting. The novel technology has been proven by extensive decontamination tests in pilot scale set-up.
The recycling process includes the following steps:

- ✓ Step 1: Grinding of post-consumer PP into flakes followed by an intensive washing process and drying; an optional flake-sorting step can be used to improve flake quality.
- ✓ Step 2: Melting by extrusion with degassing of such r-PP flakes and polymer melt filtration;
- ✓ **Step 3: Decontamination of the polymer melt (Novel Technology based on Versalis proprietary design);**
- ✓ Step 4: polymer melt feeding system to r-PP filtration and pelletizing system.

1. FOREWORDS

Versalis notifies the novel technology "Recycled Polypropylene (r-PP) Decontamination Technology" as "developer" under the Regulation 2022/1616.

Recyclers using Versalis Novel technology will produce pellets of decontaminated r-PP suitable to be used in food packaging applications in direct contact with food, according to the conditions of use and maximum recycled content justified by the evaluation.

The **process parameters, design of equipment** and **process scheme** form part of Versalis intellectual property, therefore, they should be kept **confidential**.

This document has been written following the requirements for the development of a novel technology as reported in Regulation 2022/1616 with particular reference to Article 10.

Versalis points out that the present document originally contains confidential information owned by Versalis. This confidential information have been omitted and replaced by confidentiality placeholders

2. CHARACTERIZATION OF INPUT MATERIAL

The input to the Novel Decontamination Technology consists of washed and dried post-consumer Polypropylene (here below as "PP") flakes derived from materials and articles manufactured in accordance with applicable EU food-contact legislation. Eligible feedstock includes mono-material closures/caps previously used for food contact. The feedstock shall originate from qualified and traceable sources.

The assessment covers input materials derived from PP articles obtained from separate collection of municipal waste. Representative articles include bottles caps from PET bottles.

For mechanically recycled PET, EFSA has concluded that non-food PET containers should not be intentionally introduced into the input and that the non-food fraction should not exceed 5% (EFSA, 2011)[i]. This PET-specific benchmark can be transferred to PP caps that are derived from PET bottles. So, the present notification applies the consideration that for PP caps derived from municipal separate-collection streams, more than 99% PP shall be compliant with Regulation (EU) No 10/2011 and more than 95% food-contact articles shall be contained.

This document is CONFIDENTIAL and is property of Versalis S.p.A. It shall neither be divulged to any third party nor used for purposes other than those for which it has been provided. Unless expressly authorized in writing by Versalis S.p.A. its reproduction is prohibited.

Compliance shall be demonstrated through source qualification, sorting performance, sampling and documented quality controls.

Table 1 summarizes the feedstock characteristics for closures and caps derived from separate collection of municipal waste, in particular with regards to the proportion of PP food-contact articles.

Type of collection	Example of food-contact articles	Content of food-contact articles (%)
Separate collection of municipal waste	Caps and closures, mainly from PET bottles	>95%

Table 1: *Feedstock characteristics.*

The present assessment encompasses food-contact PP input streams derived from PP caps and closures from separate collection of municipal waste, so an initial contamination level of 3 mg/kg was considered for this stream. In fact EFSA used 3 mg/kg as reference contamination level in the input of a PET recycling process[i] so, as a pragmatic approach, the same input concentration has been assumed for the safety evaluation of PP recyclates derived from caps and closures, as the source of the waste is the same of the one considered for PET recycling.

The safety conclusions and maximum recycled-content percentages are therefore application-specific and depend on the abovementioned initial contamination assumption.

The input material to the Novel Decontamination Technology is produced from waste bales or qualified PP streams. After initial sorting at municipalities or qualified sorting facilities, the material is sorted at the recycling facility using near-infrared (NIR) and/or other sorting technologies, integrated with manual sorting where necessary, to remove metals, non-PP polymers and other foreign materials. The selected PP articles are shredded or ground into flakes, subjected to density separation where applicable, hot washed, rinsed, and mechanically and thermally dried. An optional flake-sorting step may be included after washing and drying to further remove non-target materials and improve the purity of the PP flake stream. These operations remove labels, adhesives, dirt, product residues, non-target materials and other surface contaminants, yielding washed, dried and, where applicable, flake-sorted PP flakes suitable for the subsequent melt-decontamination step.

In the majority of the cases related to caps derived from PET bottles recycling, the steps of sorting, shredding and hot washing are usually managed together for caps and bottles, separation between the polyolefin material and PET are then made by gravity after washing. The polyolefin flakes so separated and dried can be further purified through flakes sorting in order to improve the flakes quality, suitable for the subsequent melt-decontamination step.

The approved input specification to the Novel Decontamination Technology defines acceptance limits for polymer composition, food-contact origin, moisture, foreign materials, visible contamination and evidence of misuse. PVC, PET, PE, PS, polyamide, multilayer structures, metals, paper, wood, labels, adhesives and other foreign materials are controlled by documentary review, sorting and, where appropriate, analytical verification. Each delivery is uniquely identified and traceable to its collection or aggregation source and is subject to documentary verification, visual inspection and a statistically justified sampling plan. Non-conforming deliveries are rejected, segregated or

This document is CONFIDENTIAL and is property of Versalis S.p.A. It shall neither be divulged to any third party nor used for purposes other than those for which it has been provided. Unless expressly authorized in writing by Versalis S.p.A. its reproduction is prohibited.

subjected to an approved corrective treatment. The washed and dried flakes to be fed to the Novel Decontamination Technology shall comply with the approved input specification, reported in Table 2:

Parameter	value
PP content	>99%
Moisture	<1%
PE content	<1%
PET content	<1%
PS content	<0.5%
PVC content	<0.5%
Polyamide content	<0.5%
Metals content	<0.1%
Wood, paper, cellulose	<0.5%

Table 2: *Input specification to the Novel Decontamination Technology.*

3. CHARACTERIZATION OF THE NOVEL TECHNOLOGY (ART. 10.3.A)

PP is a well-suited material for mechanical recycling, however recycling in food contact applications is challenging and requires processes that are capable to clean the polymer to a grade that fulfils the EFSA requirements for recycled plastics in direct food contact.

This novel technology overcomes this limit, allowing the use of r-PP in food packaging for direct contact applications according to the conditions and maximum recycled content supported by the safety evaluation.

The overall typical recycling process includes thus the following steps:

This document is CONFIDENTIAL and is property of Versalis S.p.A. It shall neither be divulged to any third party nor used for purposes other than those for which it has been provided. Unless expressly authorized in writing by Versalis S.p.A. its reproduction is prohibited.

- ✓ Step 1 (pre-treatment): Grinding and purification of the post-consumer PP stream, followed by hot washing, rinsing and drying of the flakes; an optional flake-sorting step can be used to improve flake quality.
- ✓ Step 2 (pre-treatment): Extrusion melting with degassing and melt filtration.
- ✓ **Step 3 (Novel Decontamination Technology based on Versalis proprietary design): Decontamination of the polymer melt.**
- ✓ Step 4 (post-treatment): Transfer of the decontaminated polymer melt to final filtration and pelletizing.

The Decontamination section, mentioned in step 3, is composed by CONFIDENTIAL INFORMATION.

The system will work in CONFIDENTIAL INFORMATION.

The polymer optimal residence time to reach the required decontamination efficiency is CONFIDENTIAL INFORMATION.

Typical food contact applications where the decontaminated PP could be used are beverage closures/caps, containers and trays for dairy products, beverages, meat, fruits and vegetables, and other solid or liquid food applications under the conditions supported by the safety evaluation.

The main final applications addressed by Versalis Novel technology are:

- ✓ closures/caps for mineral water bottles;
- ✓ closures/caps for softdrink bottles;
- ✓ other PP food contact articles subject to application-specific evaluation.

Application case "closures/caps for softdrink bottles" is of reference also for caps/closure for any other liquid food/beverage bottles, given the daily food consumption as referred in paragraph 4.
The storage conditions and the maximum recycled content allowed in the relevant packaging are listed in paragraph 4 and will depend on the selected final application.

Versalis Novel Technology has been designed to allow r-PP to be used in food contact applications where PP is currently used as virgin material, within the application-specific recycled content limits demonstrated by the safety evaluation.

The Novel Technology has been proven by extensive decontamination tests in pilot scale set-up.

As required by Art. 10.3.b, there are no relevant deviations from the requirements set out in Articles 6 (except Art. 6.1.a), 7 and 8 of the Regulation. In deviation from Art. 6(1a), the technology may be applied also to industrial waste originating only from materials and articles manufactured in accordance with Reg. 10/2011 or recycled plastic materials and articles manufactured in accordance with Reg. 2022/1616.

4. SCIENTIFIC EVIDENCE AND STUDIES ABOUT THE DECONTAMINATION TECHNOLOGY (ART. 10.3.C)

Versalis and the Fraunhofer-Institute IVV have been working together on the evaluation of the cleaning efficiency of this Decontamination process using Versalis' r-PP Decontamination Technology. The cleaning efficiency was experimentally verified with tests performed into an appropriate pilot scale set-up, using virgin PP intentionally contaminated with high concentrations of model substances (surrogates) according to the principles recommended by European Guidelines[i] and US FDA[ii]. The so-called challenge test was performed to study the efficiency of

This document is CONFIDENTIAL and is property of Versalis S.p.A. It shall neither be divulged to any third party nor used for purposes other than those for which it has been provided. Unless expressly authorized in writing by Versalis S.p.A. its reproduction is prohibited.

proprietary Decontamination process. All relevant process parameters as the residence time, temperature and vacuum profiles of pilot scale set-up are representative of the industrial plant process.

To evaluate the risk for the consumer, EFSA defined an evaluation procedure, which is based on the following parts:

a) Concentration of potential contaminants in post-consumer polymers;
b) Exposure scenario of the consumer;
c) Cleaning efficiencies of the Versalis' r-PP Decontamination Technology.

Regarding point a), i.e. the contamination level of recycled PP flakes before the decontamination process, a specific initial contamination level of 3 ppm is defined for the scenario considered in this assessment. The selected values are derived from conservative assumptions intended to account for the expected variability of the input streams.

The point b) is based on the EFSA criteria established for mineral water bottle caps, and soft-drink bottle caps[iii]. Additional scenarios were considered according to the specific applications of interest to the applicant.

The point c) is the core of the Novel Technology that is notified in this document, and its efficiency should be evaluated with respect to the minimum cleaning efficiencies calculated for the intended applications.

In details:

a) Input contamination level

Critical contaminants in post-consumer polymers might be chemicals from possible misuse of packaging containers, contaminants from non-food applications such as non-authorized additives as well as degradation products generated during recycling. Other contamination, such as microbiological or viral contamination, can be excluded because of the high temperatures used to process the polymer[iv].
Regarding the contamination level of recycled PP flakes prior to the decontamination process, for PP caps and closures, mainly from PET bottles, derived from separate collection of municipal waste, a conservative initial contamination level of 3 mg/kg has been considered. In fact, regarding the input contamination in recycled PP flakes before decontamination processes, scientific literature studies on misuse or contamination levels from substances from the first use of the package are rare. In the absence of a robust determination for PP, considering also that these PP articles originate from the same collection, sorting, and recycling streams as post-consumer PET bottles, the utilization of the misuse rate of PET bottles (3–4 per 10,000) would appear to be a conservative approach so, as a pragmatic approach, the same input concentration as for PET of 3 mg/kg has been assumed for the safety evaluation of PP recyclates.

b) Exposure scenario of the consumer

The exposure scenarios considered are presented in Table 3. Specifically, the table includes the following applications and associated contact conditions:

- ✓ closures for mineral water bottles (365 days at 25 °C);
- ✓ closures for soft-drink bottles (365 days at 25 °C);

To develop a more general approach, some scenarios have been evaluated at a certain Maximum Storage Time and Temperature, based on different food consumption per day.

For each exposure scenario, Table 3 reports the specific application, the concentration of potential contaminants in input (3 ppm), the geometrical characteristics used in modelling, the reference consumer group and corresponding body weight, the daily food consumption, the exposure threshold expressed as the maximum allowable migration level, and the maximum estimated migration level calculated using an overestimation factor of 2.

This document is CONFIDENTIAL and is property of Versalis S.p.A. It shall neither be divulged to any third party nor used for purposes other than those for which it has been provided. Unless expressly authorized in writing by Versalis S.p.A. its reproduction is prohibited.

Application	Concentration of potential contaminants in input	Geometrical characteristics used in modelling	Specific Food Consumption per Day	Reference consumer group	Daily Food Consumption	Maximum Storage Time and Temperature	Exposure (Maximum Migration Value)	Maximum Migration with Overestimation Factor 2
Closures for mineral water bottles	3 mg/kg	1 L bottle; closure inner surface area 3.2 cm²; closure thickness 1250 µm	260 g/ kg bw day	Infant / 5 kg bw	1300 ml/day	365 d at 25 °C	0.0095 µg/kg	**0.019 µg/kg**
Closures for softdrink bottles	3 mg/kg	1 L bottle; closure inner surface area 3.2 cm²; closure thickness 1250 µm	80 g/ kg bw day	Toddler / 12 kg bw	960 ml/day	365 d at 25 °C	0.0313 µg/kg	**0.0626 µg/kg**

Table 3: *Exposure scenarios considered in the present document. The evaluated scenarios include different daily food consumption and reference consumer group for the application "closures and caps".*

This document is CONFIDENTIAL and is property of Versalis S.p.A. It shall neither be divulged to any third party nor used for purposes other than those for which it has been provided. Unless expressly authorized in writing by Versalis S.p.A. its reproduction is prohibited.

	MW (Da)	Closures for mineral water, 365 days at 25 °C (1.3 l Infant 5 kg) - 3 mg/Kg	Closures for softdrinks, 365 days at 25 °C (960 ml Toddler 12 kg) - 3 mg/Kg
toluene	92	98.26%	94.31%
chlorobenzene	113	98.24%	94.26%
limonene	136	98.19%	94.10%
phenyl cyclohexane	160	98.08%	93.76%
benzophenone	182	97.93%	93.26%
butyl salicylate	194	97.83%	92.91%
methyl palmitate	271	96.79%	89.53%
DEHA	371	94.68%	82.64%
TEHTM	548	88.50%	62.52%
Uvinul T150	823	68.87%	0.00%

Table 4: *Calculated minimum cleaning efficiencies of the recycling process required for the scenarios listed in Table 3.*

This document is CONFIDENTIAL and is property of Versalis S.p.A. It shall neither be divulged to any third party nor used for purposes other than those for which it has been provided. Unless expressly authorized in writing by Versalis S.p.A. its reproduction is prohibited.

a) Cleaning efficiency of the decontamination process (Novel Technology)

The calculated minimum cleaning efficiencies of the recycling process required for the applications and food consumption data have been calculated by Fraunhofer-Institute IVV and are reported in Table 4.

The decontamination process shall be considered as safe if the experimental decontamination efficiencies will be equal or greater than the calculated minimum cleaning efficiencies as reported above.

The surrogates were chosen in accordance with EU relevant criteria and US FDA recommendations such that they covered the whole spectrum of physical properties and represent the different chemical and physical properties of real-life contaminants. The surrogates correspond with the following four categories of organic compounds:

- ✓ high volatile and polar
- ✓ high volatile and non-polar
- ✓ low volatile and polar
- ✓ low volatile and non-polar.

In addition, the surrogates used in the challenge test represent a variety of functional groups in order to reflect the different chemical and physical properties of real-life contaminants e.g. aliphatic and aromatic hydrocarbons, chlorinated hydrocarbons and carbonyl functional groups.

From migration theoretical considerations, the molecular weight represents a major parameter important for the selection of the surrogates. The high molecular weight substances were the most challenging substances for the investigated super-clean recycling process. Therefore, the selected surrogate set includes substances from 92.1 g/mol up to 823.1 g/mol, covering volatile and non-volatile, polar and non-polar substances relevant for PP evaluation.

Substance	Mw (g/mol)	Functional groups	Properties
Toluene	92.1	Aromatic hydrocarbon	Volatile, non-polar
Chlorobenzene	112.6	Aromatic hydrocarbon, halogen-containing	Volatile, polar
Limonene	136.2	Aliphatic hydrocarbon	Volatile, non-polar
Phenylcyclohexane	160.3	Aromatic hydrocarbon	Low volatility, non-polar
Benzophenone	182.2	Aromatic ketone	Low volatility, polar
Butyl salicylate	194.2	Aliphatic ester	Non-volatile, non-polar
Methyl palmitate	270.5	Aliphatic ester	Non-volatile, medium-polar
Diethylhexyl adipate (DEHA)	370.6	Aliphatic ester	Non-volatile, medium-polar
Tris(ethylhexyl) trimellitate (TEHTM)	546.8	Aromatic ester	Non-volatile, medium-polar
Ethylhexyl triazone (Uvinul T150)	823.1	Aromatic ester	Non-volatile, medium-polar

Table 5: *Surrogates used in the challenge test, representing a variety of functional groups, different polarities and volatile/non-volatile behavior.*

This document is CONFIDENTIAL and is property of Versalis S.p.A. It shall neither be divulged to any third party nor used for purposes other than those for which it has been provided. Unless expressly authorized in writing by Versalis S.p.A. its reproduction is prohibited.

The pressure/temperature profiles as well as the residence times... CONFIDENTIAL INFORMATION.

The contamination procedure and the analyses of the real quantities of surrogates added are reported in Attachment 1 "Fraunhofer IVV test report". The decontaminated polymer samples were sent to Fraunhofer Institute for analysis of residual surrogates. The results are reported in test report, Attachment 1 "Fraunhofer IVV test report".

The cleaning efficiency of the process for each of the applied surrogates, was calculated according to Equation 1.

$$\text{Eq. 1: } Cleaning\ efficiency = \left(1 - \frac{surrogate\ concentration\ after\ recycling}{surrogate\ concentration\ before\ recycling}\right) 100\%$$

The data reported in Attachment 1, "Fraunhofer IVV Test Report", and compared with the minimum required cleaning efficiencies, demonstrate that the Novel Technology, as Versalis r-PP Decontamination Technology, is capable of efficiently decontaminating post-consumer r-PP, reducing contaminants. The different analyzed scenarios show that the target level is not fully achieved, nevertheless the recycled material may be used at a proportion not exceeding the application-specific recycled content derived from the assessment and reported in Attachment 1. This limitation ensures that the relevant migration and exposure criteria are met.
These results therefore demonstrate the suitability of the Novel Decontamination Technology for the intended applications within the corresponding application-specific limits.
Therefore, the experimental observations deriving from the challenge test are as follows:

- ✓ the lower the pressure into the decontamination vessel, the greater the decontamination efficiency;
- ✓ the diffusivity of each species decreases as the molecular weight increases; the higher the temperature of the molten polymer, the greater the diffusivity of the contaminants to be removed;
- ✓ for obtaining high efficiencies it is necessary to manage the melt polymer flow rate and residence time inside the decontamination system to decrease the contaminants concentration.

The combination of vacuum, temperatures and residence times ensures efficient decontamination of the polypropylene without causing unacceptable degradation of the polymer properties (i.e., not appreciable variation in molecular weight nor in melt index and density).

As explained above, the applied residence times, temperatures and vacuum conditions are essential for cleaning efficiency. Therefore, these parameters are controlled and logged by a data system…CONFIDENTIAL INFORMATION.

The maximum recycled content for the different scenarios reported above have been calculated by Fraunhofer-Institute IVV and are summarized in Table 6.

Application	Concentration of potential contaminants in input [mg/kg]	Storage Conditions	Food Consumption (g/kg bw day)	Maximum Recycled Content (%)
Closures for mineral water	3	365 days at 25 °C	260	20.7%
Closures for soft drinks	3	365 days at 25 °C	80	67.4%

Table 6: *Maximum recycled content for the different scenarios listed in Table 3.*

This document is CONFIDENTIAL and is property of Versalis S.p.A. It shall neither be divulged to any third party nor used for purposes other than those for which it has been provided. Unless expressly authorized in writing by Versalis S.p.A. its reproduction is prohibited.

It can be noted that, once the relevant conditions of use are fixed — namely contact time, contact temperature, food type or simulant, reference consumer group, polymer thickness, diffusion assumptions and initial contamination level — the maximum recycled content may be treated as a parametric variable depending on the daily food consumption.
In particular, for the same reference consumer group, the same decontamination performance (i.e. same process parameters of the decontamination device), the same initial contamination level, the same food-contact conditions and the same wall thickness, the migration and the resulting recycled content in the final article scale with the daily food consumption associated with the relevant consumer scenario.

Therefore, the maximum allowable recycled content derived for one reference scenario reported in Table 6 may be extrapolated to the same application, when characterized only by a different daily food consumption, provided that the relevant use conditions remain equivalent.

Under these assumptions, the following proportionality can be applied:

$$RC_{max,ref} \times C_{ref} = RC_{max,new} \times C_{new}$$

where:

- ✓ $RC_{max,ref}$ is the maximum recycled content validated for reference scenario and reported in Table 6; it must be lower than 100%;
- ✓ C_{ref} is the daily food consumption assumed for the consumer scenario in the reference condition, reported in Table 3;
- ✓ $RC_{max,new}$ is the maximum recycled content to be calculated for the same reference scenario but with a different daily food consumption;
- ✓ C_{new} is the different daily food consumption assumed for the consumer scenario in the same reference condition.

Consequently, the maximum recycled content applicable to a scenario characterized by a daily food consumption C_{new} can be calculated as the minimum between 100% and the application of the previous correlation, i.e.:

$$RC_{max,new} = MIN\left(100\%;\ RC_{max,ref} \times \frac{C_{ref}}{C_{new}}\right)$$

The correlation allows the maximum recycled content to be adjusted in a transparent way as a function of the daily food consumption.

The above correlation should be regarded as a conservative scaling approach. Its use is appropriate only when the same polymer, the same decontamination process, the same contaminant profile, the same initial contamination assumption, the same contact conditions and the same wall thickness are maintained.

Hereafter a calculation example:

Reference scenario (Closures for soft drinks):

Food Consumption (g/kg bw day): 80 (C_{ref})
Maximum recycled content: 67.4% ($RC_{max,ref}$)

New scenario:

Application: Closures for soft drinks

This document is CONFIDENTIAL and is property of Versalis S.p.A. It shall neither be divulged to any third party nor used for purposes other than those for which it has been provided. Unless expressly authorized in writing by Versalis S.p.A. its reproduction is prohibited.

Concentration of potential contaminants in input [mg/kg]: 3
Storage Conditions: 365 days at 25 °C
Food Consumption (g/kg bw day): 41.7 (500 g/day for a 12 kg toddler) (C_{new})

Maximum recycled content for new scenario :

($RC_{max,ref}$)=MIN(100%; 67.4% x (80 / 41.7) = 129 %)=100%

Furthermore it can be noted that daily assumption is connected to the specific typology of food. As a general approach we may refer to 95th percentile consumption as per EFSA Food Consumption Database (available online: https://www.efsa.europa.eu/en/data-report/food-consumption-data).

Such database is constantly updated with new surveys; as reference, in the below Table 7 we report the updated data for some food typology.

Chronic Food Consumption Grams per day (g/day) - Consumers only EFSA Food Consumption Database*		Toddlers**
Milk and dairy products	Dairy dessert and similar	200 gr/day
Milk and dairy products	Fermented milk or cream	337 gr/day
Milk and dairy products	Cheese	166 gr/day
Coffee, cocoa, tea and infusions	Hot drinks and similar (coffee, cocoa, tea and herbal infusions)	354 gr/day
Fruit and fruit products	Processed fruit products	151 gr/day

*EFSA Food Consumption Database. Available online: https://www.efsa.europa.eu/en/data-report/foodconsumption-data .

** Food consumption considered: the maximum of 95th percentile with regards to the following Countries: Italy (survey 2017, 2018), Germany (survey 2006,2007), France (survey 2014), Spain (survey 2012, 2013), Belgium (survey 2002), Netherland (survey 2012), Portugal (survey 2015).

Table 7: *Food Consumption per day as calculated based on 95th percentile consumption as per EFSA Food Consumption Database.*

Hereafter we report a calculation example related to the consumption of "Fermented milk or cream":

Reference scenario (Closures for soft drinks):

Food Consumption (g/kg bw day): 80 (C_{ref})
Maximum recycled content: 67.4% ($RC_{max,ref}$)

New scenario:

Application: "Closure for liquid food (fermented milk or cream) bottle"

This document is CONFIDENTIAL and is property of Versalis S.p.A. It shall neither be divulged to any third party nor used for purposes other than those for which it has been provided. Unless expressly authorized in writing by Versalis S.p.A. its reproduction is prohibited.

Concentration of potential contaminants in input [mg/kg]: 3
Storage Conditions: 365 days at 25 °C
Food Consumption (g/kg bw day): 28.1 (337 g/day for a 12 kg toddler) (C_{new})

Maximum recycled content for new scenario :

(RC $_{max,ref}$)=MIN(100; 67.4% x (80 / 28.1) = 191.2 %)=100%

5. DESCRIPTION OF TYPICAL RECYCLING PROCESS USING THE TECHNOLOGY (ART. 10.3.D)

As already mentioned, the typical recycling process includes the following steps:

- ✓ Step 1 (pre-treatment): Grinding and purification of the post-consumer PP stream, followed by hot washing, rinsing and drying of the flakes; an optional flake-sorting step can be used to improve flake quality.
- ✓ Step 2 (pre-treatment): Extrusion melting with degassing and melt filtration.
- ✓ **Step 3 (Novel Technology based on Versalis proprietary design): Decontamination of the polymer melt.**
- ✓ Step 4 (post-treatment): Transfer of the decontaminated polymer melt to final filtration and pelletizing.

Recycling process scheme: CONFIDENTIAL INFORMATION.

All collection and pre-processing requirements as per Article 6 of Regulation (EU) 2022/1616 are satisfied in the recycling process.

For each production batch, representative input samples to the Novel Decontamination Technology and output samples produced with the Novel Decontamination Technology shall be collected according to a written sampling plan. Samples should be sealed and combined into representative batch composites. Each delivery shall be uniquely identified and traceable to the collection or aggregation source. Acceptance shall include documentary verification, visual inspection and a statistically justified sampling plan.

Regarding the input material, a control and management system will be adopted to ensure that the input material to the Novel Decontamination Technology is constituted at minimum by 95% PP originated from food packaging.

The control plan shall cover, as applicable: polymer composition, non-food articles, PE, PET, PS, PVC and PA content, metals, paper/cellulose/wood, moisture and evidence of misuse. Non-conforming deliveries shall be rejected, segregated or subjected to an approved corrective treatment.

The traceability will be ensured by fulfilling the EN norm 15343 “Plastics - Recycled Plastics - Plastics recycling traceability and assessment of conformity and recycled content”.

The caps are derived from PET bottles recycling, so the steps of sorting, shredding and hot washing are usually managed together for caps and bottles and separation between the polyolefin material and PET are then made by gravity after washing. The polyolefin flakes so separated and dried can be further purified through flakes sorting in order to improve the flakes quality, suitable for the subsequent melt-decontamination step.

The PP flakes shall comply with the approved input specification.

Regarding the output material, a control and management system will be adopted to ensure the quality of the produced material. Routine internal controls shall include, as applicable, volatile screening, color, melt-flow rate or

This document is CONFIDENTIAL and is property of Versalis S.p.A. It shall neither be divulged to any third party nor used for purposes other than those for which it has been provided. Unless expressly authorized in writing by Versalis S.p.A. its reproduction is prohibited.

viscosity, moisture and pellet quality. Periodic testing by competent external laboratories shall include non-targeted screening covering volatile, semi-volatile and non-volatile. The monitoring frequency shall be justified by feedstock variability, process capability and trend data and shall be increased following deviations or changes.
Known substances detected in output shall be assessed with respect to Regulation (EU) No 10/2011, restrictions or scientifically justified toxicological thresholds. Unknown substances detected in output shall be treated as measured residual concentrations and compared with an appropriate modelled or toxicological threshold. Recurrent unknowns shall trigger identification work and source investigation.

6. SUITABILITY OF THE RECYCLING TECHNOLOGY AND COMPLIANCE WITH THE RELEVANT PROVISIONS ON FOOD CONTACT MATERIALS AND ARTICLES

From the data provided in this document the following conclusions can be drawn:

- ✓ The recycling process and the Novel Technology thereof are capable to reduce the migration of potential contaminants from post-consumer PP to concentration levels which are in compliance with Article 3 of Regulation (EC) 1935/2004 for the evaluated applications and recycled content limits.
- ✓ The Novel Technology fulfils the requirements for the specific migration of the applied surrogates according to EU Regulation 10/2011.
- ✓ The investigated manufacturing process is in a position to fulfil the requirements of the GMP Regulation (EC) 2023/2006.

7. DIFFERENCES FROM EXISTING TECHNOLOGIES (ART. 10.3.E)

The technology has not been subjected to a decision on its suitability. Due to the state of the implementation of Regulation 2022/1616, the extent to which it differs from any other technology cannot been known at the time of the notification.
According to our knowledge, currently the availability of r-PP grades suitable for direct food contact is very limited; this technology allows the use of r-PP in food packaging (direct contact) under the evaluated conditions.

8. SUMMARY OF EVALUATION CRITERIA (ART. 10.3.F)

Proposed evaluation criteria for decontamination section are the following process parameters... CONFIDENTIAL INFORMATION.

These parameters will be reported in the compliance monitoring summary sheet established in accordance with Article 26 of Regulation (EU) 2022/1616.

9. LIST OF DECONTAMINATION INSTALLATIONS (ART. 10.3.G)

The first Versalis Decontamination system for r-PP, at full scale level, will be listed in this section when the installation details are finalized. The recycler, site address, nominal capacity and implementation date will be communicated when available.

The present novel technology is quite flexible in terms of flowrate.
Equipment with nominal capacity from 500 kg/h to 5000 kg/h will be proposed to the market.

This document is CONFIDENTIAL and is property of Versalis S.p.A. It shall neither be divulged to any third party nor used for purposes other than those for which it has been provided. Unless expressly authorized in writing by Versalis S.p.A. its reproduction is prohibited.

References

[i] EFSA CEF Panel (EFSA Panel on Food Contact Materials, Enzymes, Flavourings and Processing Aids). Scientific Opinion on the criteria to be used for safety evaluation of a mechanical recycling process to produce recycled PET intended to be used for manufacture of materials and articles in contact with food. EFSA J. 2011, 9, 2184.

[ii] https://www.fda.gov/FoodGuidances - Use of Recycled Plastics in Food Packaging (Chemistry Considerations): Guidance for Industry, July 2021.

[iii] Scientific Guidance on the criteria for the evaluation and on the preparation of applications for the safety assessment of post-consumer mechanical PET recycling processes intended to be used for manufacture of materials and articles in contact with food, EFSA J. 2024, 22, 8879.

[iv] F. Welle, Recycling of Post-Consumer Polystyrene Packaging Waste into New Food Packaging Applications—Part 1: Direct Food Contact. Recycling 2023, 8, 26. https://doi.org/10.3390/recycling8010026

This document is CONFIDENTIAL and is property of Versalis S.p.A. It shall neither be divulged to any third party nor used for purposes other than those for which it has been provided. Unless expressly authorized in writing by Versalis S.p.A. its reproduction is prohibited.

ATTACHMENT 1: FRAUNHOFER IVV TEST REPORT

This document is CONFIDENTIAL and is property of Versalis S.p.A. It shall neither be divulged to any third party nor used for purposes other than those for which it has been provided. Unless expressly authorized in writing by Versalis S.p.A. its reproduction is prohibited.