



DUTRAL[®]

EP(D)M

BTX(*) 4055

Ethylene - Propylene - Diene Terpolymer

(*) Experimental Grade (BTX/R = Branched Terpolymer)



Dutral[®] BTX 4055 is an Ethylene - Propylene - Diene polymer produced by suspension polymerisation using an improved Ziegler-Natta Catalyst at the Ferrara production facility in Italy. A non-staining antioxidant is added during the production process.

Main Properties	Unit	Value
Mooney Viscosity ML 1+4(100 °C)	MU	45
Volatiles content	% wt	0.5 max
Ash content	% wt	0.3 max
Propylene content	% wt	45
ENB content	% wt	4,2

Key Features

Dutral[®] elastomers are characterized by excellent resistance to ageing and weathering, good resistance to both high and low temperatures, low permanent set values, good resistance to a large number of chemicals.

Dutral[®] BTX 4055 is a low molecular weight terpolymer of medium diene content.

It is characterized by tailored molecular structure to improve mixing ability, good mechanical properties and good collapse resistance.

Dutral[®] BTX 4055 based compounds exhibit good injection molding performance, good curing rate and excellent low temperature behaviour.

Main Applications

Automotive brake system, Mechanical Goods for injection molding

Physical Form

Bales wrapped with low melting point polyethylene film; typical bale weight: 25 kg.

Packaging

Cardboard box of 625 kg containing 25 bales (1050 x 1250 x h1050 mm).

Storage Conditions

Store in dry and vented areas, avoiding temperatures above 35 °C and direct sunlight.

It is recommended that temperatures above 30 °C be avoided for prolonged storage times in order to not deteriorate the quality of the product and reduce its shelf life.

Shelf life : 36 months.

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, expressed or implied, is made nor liability accepted with respect to the use of such information and data.