



versalis

[www.versalis.eni.com](http://www.versalis.eni.com)

## Technical Data Sheet

[info.elastomers@versalis.eni.com](mailto:info.elastomers@versalis.eni.com)

### DUTRAL<sup>®</sup>

EP(D)M

### CO 058

Ethylene - Propylene Copolymer

Dutral<sup>®</sup> CO 058 is an Ethylene - Propylene polymer produced by suspension polymerisation using a Ziegler-Natta Catalyst at the Ferrara production facility in Italy.  
A non-staining antioxidant is added during the production process.

#### Main Properties

#### Unit

#### Typical Value

Mooney Viscosity ML 1+4(100 °C)	MU	80
Volatiles content	% wt	0.5 max
Ash content	% wt	0.3 max
Propylene content	% wt	48

#### Key Features

Dutral<sup>®</sup> elastomers are characterized by excellent resistance to ageing and weathering, good resistance to both high and low temperatures, low permanent set values, good resistance to a large number of chemicals.

Dutral<sup>®</sup> CO 058 is an amorphous copolymer of medium-high molecular weight.

Articles based on Dutral<sup>®</sup> CO 058 are characterized by superior cold flexibility.

#### Main Applications

Appliances, polymer modification, oil viscosity modifier.

#### Physical Form

Bales wrapped with low melting point, oil dissolvable ethylene vinyl acetate copolymer film, typical bale weight: 25 kg.

#### Packaging

Cardboard box of 625 kg containing 25 bales wrapped with polyethylene film (1070 x 1270 x h1050 mm).

#### Storage Conditions

Store in dry and vented areas, avoiding temperatures above 35 °C and direct sunlight.

It is recommended that temperatures above 30 °C be avoided for prolonged storage times in order to not deteriorate the quality of the product and reduce its shelf life.

Shelf life : 36 months.

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, expressed or implied, is made nor liability accepted with respect to the use of such information and data.