

**DUTRAL<sup>®</sup>**

EP(D)M

**TER 4437**

Ethylene - Propylene - Diene Terpolymer

Dutral<sup>®</sup> TER 4437 is an Ethylene - Propylene - Diene polymer produced by suspension polymerisation using a Ziegler-Natta Catalyst at the Ferrara production facility in Italy.  
A non-staining antioxidant is added during the production process.

**Main Properties****Unit****Typical Value**

Mooney Viscosity ML 1+4(125 °C)	MU	57
Volatiles content	% wt	0.5 max
Ash content	% wt	0.3 max
Propylene content	% wt	32 <sup>(1)</sup>
ENB content	% wt	4.5 <sup>(1)</sup>
Oil content	% wt	40

<sup>(1)</sup> Referred to polymer matrix

**Key Features**

Dutral<sup>®</sup> elastomers are characterized by excellent resistance to ageing and weathering, good resistance to both high and low temperatures, low permanent set values, good resistance to a large number of chemicals.

Dutral<sup>®</sup> TER 4437 is a very high molecular weight terpolymer of medium diene content, extended with 40% paraffinic oil.

It is characterized by high loading capacity, good dimensional stability, easier dispersion of ingredients during mixing and enhanced low temperature elasticity compared with Dutral<sup>®</sup> TER 4436.

**Main Applications**

Automotive, mechanical goods, appliances, TPV.

**Physical Form**

Bales wrapped with low melting point polyethylene film; typical bale weight: 25 kg.

**Packaging**

Cardboard box of 750 kg containing 30 bales (1050 x 1250 x h1050 mm).

**Storage Conditions**

Store in dry and vented areas, avoiding temperatures above 35 °C and direct sunlight.

It is recommended that temperatures above 30 °C be avoided for prolonged storage times in order to not deteriorate the quality of the product and reduce its shelf life.

Shelf life : 36 months.

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, expressed or implied, is made nor liability accepted with respect to the use of such information and data.