



# Europrene® Latices

SB LATEX

**1152**

Carboxylated Styrene – Butadiene Copolymer

Europrene® Latices 1152 is an aqueous dispersion of a modified carboxylated styrene-butadiene copolymer obtained using synthetic anionic emulsifiers.

Main Properties	Test Method	Unit	Typical Value
Total solid content	ASTM D 1417	% wt	50
Brookfield Viscosity 20 rpm, 25°C	ASTM D 1417	mPa.s	220
Surface Tension	ASTM D 1417	mN/m	48
pH	ASTM D 1417		6.2

## Key Features

Europrene® Latices 1152 is completely ammonia free. It is a medium stiffness polymer offering an excellent good binding stability power and good coater runnability. It can be used alone or with fillers such as calcium carbonate/kaolin.

## Main Applications

Europrene® Latices 1152 is a binder which, in combination with all coating pigments, is used for the finishing of the pre and top coated paper. It has a high latex stability and good printability for offset, web offset paper and board coating.

## Physical Form

At standard condition (T=25 °C P=1 bar) is liquid, color white or milky white.

## Packaging

Europrene® Latices 1152 is delivered in road tankers/flexitank (bulk) and IBC (1000 l).

## Storage Conditions

Store in closed vented tanks or in a covered place in sealed packaging, away from sunlight and heat sources, at temperature between +5°C and +40°C. The water dispersion should be stirred before use. The shelf life is 6 months minimum.

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information data.

® Registered Trademark