



Technical Data Sheet

Europrene® Latice

XSB LATEX

5587 BCA

Styrene – Butadiene Copolymer Bio-Circular Attributed



Europrene® Latice 5587 BCA is an aqueous dispersion of a modified carboxylated styrene-butadiene copolymer obtained using synthetic anionic emulsifiers. It contains a non staining antioxidant.

Sustainability

Bio raw materials can be used in production processes together with traditional raw materials. In order to attribute sustainability characteristics to the final product, Versalis applies the **Mass Balance** approach, an acknowledged methodology that ensures that the sustainability characteristics of the alternative raw material, mixed with traditional naphtha, correspond to those of the final product. BCA products are provided with a **sustainability declaration** indicating the amount of Bio-Circular Attributed component. They guarantee identical performance, quality and properties, as they do not differ in chemical composition and physical-mechanical performance from standard products.

Main Properties	Test Method	Unit	Typical Value
Total solid content	ASTM D 1417	% wt	50
Brookfield Viscosity 20 rpm, 25°C	ASTM D 1417	mPa.s	600
Bound Styrene	ASTM D 5775	% wt	75
pH	ASTM D 1417		7.5

Key Features

Europrene® Latice 5587 BCA is completely ammonia free. It is a functional polymer with very firm handle and can be used alone or with most common fillers; the viscosity of compounds can be adjusted to the desired level using a standard thickener. It can be used for stiffening other carboxylated latices.

Main Applications

Europrene® Latice 5587 BCA is used for textile application when a very firm handle is required.

Physical Form

At standard condition (T=25 °C P=1 bar) is liquid, color white or milky white.

Packaging

Europrene® Latice 5587 BA is delivered in bulk using tank trucks, flexitank and IBC (1000 l.)

Storage Conditions

Store in closed vented tanks or in a covered place in sealed packaging, away from sunlight and heat sources, at temperature between +5°C and +40°C. The water dispersion should be stirred before use. The shelf life is 6 months minimum.

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge, true and accurate, but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information data.

© Registered Trademark