



Europrene® Lattice

XSB LATEX

5587

Carboxylated Styrene – Butadiene Copolymer

Europrene® Lattice 5587 is an aqueous dispersion of a modified carboxylated styrene-butadiene copolymer obtained using synthetic anionic emulsifiers. It contains a non staining antioxidant.

Main Properties	Test Method	Unit	Typical Value
Total solid content	ASTM D 1417	% wt	50
Brookfield Viscosity 20 rpm, 25°C	ASTM D 1417	mPa.s	600
Bound styrene	ASTM D 2775	% wt	75
pH	ASTM D 1417		7.5

Key Features

Europrene® Lattice 5587 is completely ammonia free. It is a functional polymer with very firm handle and can be used alone or with most common fillers; the viscosity of compounds can be adjusted to the desired level using a standard thickener. It can be used for stiffening other carboxylated latices.

Main Applications

Europrene® Lattice 5587 is used for textile application when a very firm handle is required.

Physical Form

At standard condition (T=25 °C P=1 bar) is liquid, color white or milky white.

Packaging

Europrene® Lattice 5587 is delivered in road tankers/flexitank (bulk) and IBC (1000 l.).

Storage Conditions

Store in closed vented tanks or in a covered place in sealed packaging, away from sunlight and heat sources, at temperature between +5°C and +40°C. The water dispersion should be stirred before use. The shelf life is 6 months minimum.

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information data.

® Registered Trademark