

EUROPRENE® S-SBR

SOL R X⁽¹⁾ 71420

Styrene - Butadiene Copolymer
functionalized for carbon black
(1) Experimental Grade

Europrene® SOL R X 71420 is a solution polymerized, dry styrene-butadiene random copolymer.
A non-staining antioxidant is added during the production process.

Main Properties	Test Method	Unit	Typical Value
Mooney Viscosity ML 1+4(100 °C)	ASTM D 1646	MU	58
Bound Styrene	Internal Method	% wt	15
Vinyl content	Internal Method	% wt	48 ⁽¹⁾
Volatile Matter	ASTM D 5668	% wt	0.75 max
Tg	Internal Method	°C	-50

⁽¹⁾ Referred to butadiene portion

Key Features

Europrene® SOL R X 71420 is designed to provide good low temperature properties. Its micro- and macrostructure make it suitable for low glass transition temperature compounds with good mechanical properties.

Main Applications

Tyre treads compounds with low rolling resistance. It is suitable for medium-heavy commercial vehicles tyre treads compounds.

Physical Form

Clear bales wrapped in easily dispersible polyethylene film.

Packaging

Returnable metal crate, nominal net weight 990 kg; 33 kg bale, 30 bales per crate (1465 x 1150 x H1123 mm).
On request available in wooden crate: nominal net weight 990 kg; 33 kg bale, 30 bales per crate (1490 x 1150 x H975 mm).

Storage Conditions

Store in a vented, dry area at temperatures between 20°C and 30°C; no direct sunlight.
Shelf life: 24 months minimum.

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information data.