



## Technical Data Sheet

# Europrene® SBS

# SOL T 161 C

Styrene/Butadiene Block Copolymer

Europrene® SOL T 161C is a radial block copolymer obtained by anionic polymerization. The polymer is based on styrene and butadiene. A non-staining antioxidant system is added during the production process.

Main Properties	Test Method	Unit	Typical Value
Bound Styrene Content	Internal Method	% wt	30
Specific gravity	ASTM D 792	g/cc	0,94
Melt Flow Index*	ASTM D 1238	g/10 min	<1
Volatile Matter	ASTM D 5668	%	1 max
Hardness**	ASTM D 2240	Sh A	82
Brookfield Viscosity***	Internal Method	Pa · s	8,2

\*190°C, 5 kg

\*\*Measured on ASTM D 4703 compression molded specimens

\*\*\*Xylene sol., 25% wt

## Key Features

Europrene® SOL T 161C is a block copolymer with radial molecular structure, providing excellent mechanical properties, high strength and elasticity in a wide range of formulated products.

## Main Applications

Used in bitumen modification in waterproofing membranes and road paving. The grade is also used in formulated compounds for footwear and technical applications.

## Physical Form

Europrene® SOL T 161C is produced in Ravenna Plant (Italy) in granule form (G).

## Packaging

Available in bags on pallet and big bags. For detailed information, please refer to your Versalis representative.

## Storage Conditions

Store the preparation in a covered place in sealed packaging, away from sunlight and heat sources. Ensure the proper ventilation in all storage areas.

Shelf life: 18 months

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information and data.

® Registered Trademark