



Europrene®

SOL T 166 BA

Styrene/Butadiene Block Copolymer Bio Attributed





Europrene® SOL T 166 BA is a linear block copolymer obtained by anionic polymerization. The polymer is based on styrene and butadiene. A non-staining antioxidant system is added during the production process.

Sustainability

Bio raw materials can be used in production processes together with traditional raw materials. In order to attribute sustainability characteristics to the final product, Versalis applies the Mass Balance approach, an acknowledged methodology that ensures that the sustainability characteristics of the alternative raw material, mixed with traditional naphtha, correspond to those of the final product. BA products are provided with a sustainability declaration indicating the amount of Bio Attributed component. They guarantee identical performance, quality and properties, as they do not differ in chemical composition and physical-mechanical performance from standard products.

Main Properties	Test Method	Unit	Typical Value
Bound Styrene Content	Internal Method	% wt	30
Diblock Content	Internal Method	% wt	10
Melt Flow Index*	ASTM D 1238	g/10 min	6
Volatile Matter	ASTM D 5668	%	1 max
Specific gravity	ASTM D 792	g/cc	0,94
Brookfield Viscosity**	Internal Method	Pa·s	1,0

^{*190°}C, 5 kg

Key Features

Europrene® SOL T 166 BA is a linear block copolymer, providing excellent dispersibility and processability, combined with high strength and elasticity.

Main Applications

Characterized by the excellent dispersibility and processability, the grade is widely used in adhesive formulated products, in compounding for both footwear and technical applications and as a toughening agent in polymer modification and plastic recycling.

Physical Form

Europrene® SOL T 166 BA is produced in Ravenna Plant (Italy) in pellet form.

Packaging

Available in standard packaging. For detailed information, please refer to your Versalis representative.

Storage Conditions

Store the preparation in a covered place in sealed packaging, away from sunlight and heat sources. Ensure the proper ventilation in all storage areas.

Shelf life: 18 months

^{**}Xylene sol., 25% wt





Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, $expressed \ or \ implied, is \ made \ nor \ is \ any \ liability \ accepted \ with \ respect \ to \ the \ use \ of \ such \ information \ and \ data.$

® Registered Trademark