



Technical Data Sheet

Europrene®
SBS

SOL T 6302 BA
Styrene/Butadiene Block Copolymer Bio Attributed



Europrene® SOL T 6302 BA is a linear block copolymer obtained by anionic polymerization. The polymer is based on styrene and butadiene. A non-staining antioxidant system is added during the production process.

Sustainability

Bio raw materials can be used in production processes together with traditional raw materials. In order to attribute sustainability characteristics to the final product, Versalis applies the **Mass Balance** approach, an acknowledged methodology that ensures that the sustainability characteristics of the alternative raw material, mixed with traditional naphtha, correspond to those of the final product. BA products are provided with a **sustainability declaration** indicating the amount of Bio Attributed component. They guarantee identical performance, quality and properties, as they do not differ in chemical composition and physical-mechanical performance from standard products.

Main Properties	Test Method	Unit	Typical Value
Bound Styrene Content	Internal Method	% wt	30
Specific gravity	ASTM D 792	g/cc	0,94
Melt Flow Index*	ASTM D 1238	g/10 min	<1
Volatile Matter	ASTM D 5668	%	1 max
Hardness**	ASTM D 2240	Sh A	80
Brookfield Viscosity***	Internal Method	Pa · s	6,3

*190°C, 5 kg

**Measured on ASTM D 4703 compression molded specimens

***Xylene sol., 25% wt

Key Features

Europrene® SOL T 6302 BA is a linear block copolymer, providing excellent mechanical properties, high strength and elasticity, combined with good dispersibility and processability.

Main Applications

Used in bitumen modification, particularly in road paving applications, in compounding for both footwear and technical goods.

Physical Form

Europrene® SOL T 6302 BA is produced in Ravenna Plant (Italy) in granule form (G).

Packaging

Available in standard packaging. For detailed information, please refer to your Versalis representative.

Storage Conditions

Store the preparation in a covered place in sealed packaging, away from sunlight and heat sources. Ensure the proper ventilation in all storage areas.

Shelf life: 18 months

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information and data.

® Registered Trademark