



Europrene®

SOL T 172 C BCA

Styrene/Butadiene Block Copolymer Bio-Circular Attributed





Europrene® SOL T 172 C BCA is a radial block copolymer obtained by anionic polymerization. The polymer is based on styrene and butadiene. The polymer is extended with a clear paraffinic oil (45 phr). A non-staining, TNPP free antioxidant system is added during the production process.

Sustainability

Bio-Circular raw materials can be used in production processes together with traditional raw materials. In order to attribute sustainability characteristics to the final product, Versalis applies the Mass Balance approach, an acknowledged methodology that ensures that the sustainability characteristics of the alternative raw material, mixed with traditional naphtha, correspond to those of the final product. BCA products are provided with a sustainability declaration indicating the amount of Bio-Circular Attributed component. They guarantee identical performance, quality and properties, as they do not differ in chemical composition and physical-mechanical performance from standard products.

| Main Properties | Test Method | Unit | Typical Value |
|-----------------------|-----------------|----------|---------------|
| Bound Styrene Content | Internal Method | % wt | 31 |
| Melt Flow Index* | ASTM D 1238 | g/10 min | 9,0 |
| Hardness** | ASTM D 2240 | Sh A | 48 |
| Volatile Matter | ASTM D 5668 | % | 0,6 max |
| Specific gravity | ASTM D 792 | g/cc | 0,92 |

^{*190°}C. 5 ka

Key Features

Europrene® SOL T 172 C BCA is a block copolymer with radial molecular structure, where the oil addition allows extremely good flow characteristics and an easy processability. The grade provides excellent mechanical properties and outstanding abrasion resistance, in a wide range of formulated products. The clear paraffinic oil allows to get finished items with excellent color stability.

Main Applications

The polymer is used as a high strength base in formulated compounds for footwear and technical applications.

Physical Form

Europrene® SOL T 172 C BCA is produced in Ravenna Plant (Italy) in pellet form.

Packaging

Available in standard packaging. For detailed information, please refer to your Versalis representative.

Storage Conditions

Store the preparation in a covered place in sealed packaging, away from sunlight and heat sources. Ensure the proper ventilation in all storage areas.

Shelf life: 18 months

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee. expressed or implied, is made nor is any liability accepted with respect to the use of such information and data.

® Registered Trademark

^{**}Measured on ASTM D 4703 compression molded specimens